

---

Lazer LXII is a UV curable ink specifically formulated for printing on many difficult to adhere to surfaces. LXII has the ability to adhere, without the use of additives, to fluted polypropylene and high density polyethylene. LXII also offers excellent water resistance without the use of waste producing additives.

---

## Performance Properties

- Adhesion to fluted plastic signage and most coated metals
- Water resistant without additives
- Large range of standard opaque colors
- Durable, scratch resistant film
- Superior print quality
- Solar Shield Clear for extended outdoor durability

## Printing

Mix well prior to use. While supplied in press ready condition, LXII may be reduced up to 10% with LXII Thinner for special viscosity adjustments.

Care should be taken to print the ink at optimal temperature 70-90°F (21-27°C). Cool ink will have heavier viscosity and will not flow properly whereas hot ink will be lower in viscosity resulting in poor definition and decreased opacity.

## Coverage

3,200 to 3,600 square feet per gallon based on ink deposit of .40-.60 mil dependant on color and printing conditions.

## Curing

Ink will cure well when printed through 355 (140cm) plain weave polyester mesh or finer. LXII's optimal cure window of 175-200 mJ / 550-650 mW is generally achieved with one 200 watt per inch mercury vapor lamp at belt speeds between 50-60 feet per minute (20-30 m/min). Cure speeds may vary as thicker material and dark surface colors require more energy. HDPE requires 350 mJ's achieved with one 300 watt bulb at 30 feet (10 m).

Adhesion should be a minimum of 95% from curing unit with final adhesion developing within four hours of initial polymerization. Coarser fabrics can be utilized; however, cure parameters may need to be adjusted for increased ink film.

If a loss of gloss or adhesion due to insufficient cure is noticed, the use of 5-10% LXII Mixing Clear will increase light penetration and improve cure.

## A. Warranty Liability Limited to Purchase and Installation Costs

Notwithstanding anything provided herein or any other written material to the contrary, Polymeric only warrants the purchase price and costs of installation. POLYMERIC SHALL HAVE NO LIABILITY OR OBLIGATION TO ANY USER, BUYER, PURCHASER, DISTRIBUTOR OR OTHER PERSON OR ENTITY FOR ANY SPECIAL, DIRECT, INDIRECT, INCIDENTAL, OR CONSEQUENTIAL DAMAGES, HOWEVER CAUSED, INCLUDING WITHOUT LIMITATION, PERSONAL INJURY, LOSS OF BUSINESS, LOSS OF PROFIT, OR OTHER DAMAGE, whether or not buyer shall have informed Polymeric of the possibility or likelihood of any such damages.

## B. Limitation of Implied Warranty and Fitness for a Particular Purpose

POLYMERIC'S WARRANTY IS GIVEN IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO AN IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, AN IMPLIED WARRANTY OF MERCHANTABILITY, AND ANY OTHER IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, PERFORMANCE, CUSTOMER USAGE OR TRADE.

**MIX WELL BEFORE USE.** Follow any indications on the package, ask for the safety data sheets and always follow the indications contained therein. In case of doubt, please contact our Technical Service department

## Recommended Substrates

- Fluted Polypropylene
- High Density Polyethylene
- Anodized Aluminum
- ABS
- Rigid Vinyl
- Acrylic (Plexiglass®)
- Polystyrene
- Many coated metals

## Lightfastness

LXII is lightfast up to one (1) year with a 355/inch or coarser mesh. Weathering tests have been completed and the ink withstood 500 hours of exposure with 4-hour cycle times of light and condensation at elevated temperatures with minimal color change and no shrinkage. To maintain a high gloss finish use LXII Overprint Clear.

Accelerated machine weathering are reference standards and can not precisely reproduce actual outdoor performance. Based on prior correlation of accelerated testing vs. real time exposure, 500 hours is equated to approximately one year, 45° south Florida

Water resistance is required for most outdoor applications, tests should be conducted at a minimum of 24 hours after curing. If additional water resistance is required, use 3% -5% of #2153 adhesion Promoter.

## Solar Shield Clear

UV absorbers have been incorporated into the LXII Solar Shield Overprint clear, which lengthen the graphics life by acting as a sunscreen. This clear requires more energy to cure than the normal Lazer LXII color range. A minimum of 225-250 mJ is needed.

**Storage**

Care should be taken to store ink in tightly closed containers located in a cool (60-80°F/15-27°C) dark place. After long production runs excess ink from the screen should be properly disposed. With suitable conditions, unopened ink is expected to have a shelf life of approximately twelve (12) months from date of manufacture.

**Metallics**

Use the Metallic Mixing Clear to prepare metallic ink as it's increased viscosity helps insure a good particle suspension and extended shelf life. Recommended mixing ratios, by weight are:

- 28% gold paste
- 12% silver paste

For optimum coverage and opacity, 280-305 (110-120cm) plain weave mesh is recommended. Use LXII Overprint Clear for extended weatherability and improved non-tarnishing properties of the product.

**Additives**

- 7779 Thinner up to 10% as needed
- 2153 Adhesion Promoter, 3-5% as needed

**Precautions**

Read the material safety data sheet prior to processing. It contains instructions for precautions when handling inks. If ink comes in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent). Wash and rinse the affected area with soap and water.

**Process Printing**

For superior halftone reproduction, Lazer LXII halftones are available in a range of density levels. Additional control of density may be achieved with use of LXII HT Base. For best results, 380 (150 cm) or finer and a smooth, thin stencil coating should be utilized with process printing.

	Press Ready	High Density	Backlit Density
LXII Halftone Yellow	0.90	1.10	1.35
LXII Halftone Magenta	1.40	1.75	2.05
LXII Halftone Cyan	1.40	1.80	2.20
LXII Halftone Black	1.60	2.00	2.25

**Color Availability**

Lazer LXII is available in twenty opaque standard colors. Custom matches, metallic, fluorescent and transparent colors are obtainable upon request.

LXII-101 Primrose Yellow	LXII-210 Ultra Blue
LXII-111 Lemon Yellow	LXII-220 Emerald Green
LXII-123 Medium Yellow	LXII-225 Forest Green
LXII-131 Brilliant Orange	LXII-226 Lime Green
LXII-135 Vivid Orange	LXII-235 Teal
LXII-141 Fire Red	LXII-240 Purple
LXII-151 Scarlet Red	LXII-260 Brown
LXII-155 Rubine Red	LXII-301 Opaque Black
LXII-160 Rhodamine Red	LXII-311 Opaque White
LXII-180 Warm Red	LXII-312 Dense Black
LXII-190 Process Blue	LXII-026 Brilliant White
LXII-200 Peacock Blue	LXII Overprint Clear
LXII-205 Reflex Blue	LXII Metallic Mixing Clear

**Pantone Matching System® Colors**

The nine PANTONE® approved Color Matching System (CMS) shades are used to simulate the PANTONE Color Specifier colors. Formulas were designed for maximum opacity and are available in book or Imaging Color Source Software formats.

LXII-064 CMS GS Yellow
LXII-066 CMS RS Yellow
LXII-114 CMS Orange
LXII-121 CMS YS Red
LXII-164 CMS BS Red
LXII-165 CMS Magenta
LXII-127 CMS Violet
LXII-230 CMS Blue
LXII-325 CMS Green
LXII Tinting White
LXII Shading Black
LXII Mixing Clear

PANTONE® is a trademark of Pantone, Inc. Portions © Pantone, Inc., 1963, 1991.

**A. Warranty Liability Limited to Purchase and Installation Costs**

Notwithstanding anything provided herein or any other written material to the contrary, Polymeric only warrants the purchase price and costs of installation. POLYMERIC SHALL HAVE NO LIABILITY OR OBLIGATION TO ANY USER, BUYER, PURCHASER, DISTRIBUTOR OR OTHER PERSON OR ENTITY FOR ANY SPECIAL, DIRECT, INDIRECT, INCIDENTAL, OR CONSEQUENTIAL DAMAGES, HOWEVER CAUSED, INCLUDING WITHOUT LIMITATION, PERSONAL INJURY, LOSS OF BUSINESS, LOSS OF PROFIT, OR OTHER DAMAGE, whether or not buyer shall have informed Polymeric of the possibility or likelihood of any such damages.

**B. Limitation of Implied Warranty and Fitness for a Particular Purpose**

POLYMERIC'S WARRANTY IS GIVEN IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO AN IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, AN IMPLIED WARRANTY OF MERCHANTABILITY, AND ANY OTHER IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, PERFORMANCE, CUSTOMER USAGE OR TRADE.

MIX WELL BEFORE USE. Follow any indications on the package, ask for the safety data sheets and always follow the indications contained therein. In case of doubt, please contact our Technical Service department